



SGS U.S. Testing Company Inc.

5555 Telegraph Road
Los Angeles, CA 90040
Tel: 213 838-1600
Fax: 213 722-8251

REPORT NUMBER: 720210-3R
DATE: 12/24/96
PAGE 1 OF 12
REVISED DATE: 03/04/97

CLIENT: DOC'S MARKETING CORPORATION
2343 Calle Alucema
Thousand Oaks, CA 91360

SUBJECT: METAL/WOOD SCREW (150 SP)

REFERENCES: Conferences and correspondence with Mr. Forrest Dockery commencing September 18, 1995.

SAMPLE ID: The following specimens were randomly sampled at Doc's Marketing Corporation, 5158 Goldman Ave. Unit A, Moorpark, CA 93021, by an SGS United States Testing Co. representative on October 7, 1996:

- 225 ea, 2³/₄-inch long, nominal, heat-treated, plated, 1018 steel, ceiling suspension fasteners, Part Number 150SP. Each fastener consisted of a 1¹/₂-inch long threaded portion (0.19-inch shank diameter; 0.25-inch thread diameter), a 0.5-inch diameter by 0.08-inch thick washer portion, a 0.21-inch diameter by 0.6-inch long shank portion and a 0.08-inch thick by 0.5-inch long flattened, eyelet portion with a 0.18-inch diameter hole. The underside of the collar portion had a fan blade appearance and the top had four lines radiating from the center (See drawing in the Appendix).

The Client submitted 22-gauge, corrugated, galvanized, sheet metal sections and identified them as being manufactured by Verco, ICBO #2078.

The Rockwell C hardness of the sampled fasteners was 39, as determined by Metal Control Laboratories, Inc. in Montebello, CA, and witnessed by SGS U.S. Testing Company personnel, on November 26, 1996.


The chemical composition of a specimen taken from the sampled lot was determined by the Client and the report, from MGF Wire Processing Industries, Inc., is included in the Appendix.

REPORT OF TEST


Marco Tachiquin
Test Engineer

Member of the SGS Group

SIGNED FOR THE COMPANY:


David Pereg
Manager, Engr. Dept.

